

PGS® Series

Synthetic natural gas compressor



Your benefits at a glance

- Extends drain intervals and parts life
- Contains rust and corrosion inhibitors
- Contains oxidation control agents, anti-wear compounds and hydrogen sulfide inhibitors

Your requirements - our solution

Summit PGS synthetic lubricants are polyalkylene glycol based products for use in natural gas rotary screw compressors. The resistance to thinning out by hydrocarbon dilution allows PGS to maintain the proper operating viscosity, extending drain intervals and parts life. This unique blend is specifically additive treated with rust and corrosion inhibitors, oxidation control agents, anti-wear compounds, and hydrogen sulfide inhibitors. Contact your Summit representative for specific product recommendations.

Application

Natural gas rotary screw compressors

Application notes

As the Summit PGS lubricants are incompatible with petroleum oils, care should be taken to make sure the two are not mixed.

Material safety data sheets

Material safety data sheets can be requested via our website <https://www.klsummit.com>. You may also obtain them through your contact person at Summit Lubrication.

Characteristics	PGS-32	PGS-46	PGS-68	PGS-100
Article number	340354	340217	340108	340101
Density	1.015 g/cm ³	1.024 g/cm ³	-	-
Density, 20°C	-	-	approx. 1.038 g/cm ³	approx. 1.047 g/cm ³
Flash point	205 °C	257 °C	-	-
Flash point, ASTM D92, Cleveland open cup	-	-	≥ 230 °C	≥ 230 °C
Kinematic viscosity, 100°C	6.9 mm ² /s	9.9 mm ² /s	-	-
Kinematic viscosity, 40°C	30.4 mm ² /s	47.0 mm ² /s	-	-
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	-	-	approx. 13.9 mm ² /s	approx. 19.5 mm ² /s
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	-	-	approx. 68 mm ² /s	approx. 101 mm ² /s
Viscosity index	198	204	-	-
Viscosity index, ASTM D2270	-	-	approx. 211	approx. 216
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346	-	-	approx. -52 °C	approx. -48 °C
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-60 °C	-51 °C	-	-

PGS® Series

Synthetic natural gas compressor



Characteristics	PGS-32	PGS-46	PGS-68	PGS-100
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months	36 months	36 months	36 months

Characteristics	PGS-150
Article number	340103
Density	-
Density, 20°C	approx. 1.059 g/cm ³
Flash point	-
Flash point, ASTM D92, Cleveland open cup	≥ 240 °C
Kinematic viscosity, 100°C	-
Kinematic viscosity, 40°C	-
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approx. 27.4 mm ² /s
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approx. 150 mm ² /s
Viscosity index	-
Viscosity index, ASTM D2270	approx. 221
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346	approx. -45 °C
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	36 months

PGS® Series

Synthetic natural gas compressor



Summit Lubrication

Your expert in specialty lubricants. Since 1982, we have partnered with you to bring you the right solution and advanced lubrication technologies. With over 500 products, from air and gas compressor oils to refrigeration oils, we develop top-of-the-line products tailored to your specific needs. Your success is our success.

Summit Lubrication a brand of Klüber Lubrication NA LP /
9010 County Road 2120, Tyler, TX 75707 /
Phone: +1 800 749 5823 / www.klsupport.com

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication NA LP. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication NA LP and if source is indicated and voucher copy is forwarded.