Información de producto

RPE Series

Hojas de datos de seguridad

Las hojas de datos de seguridad actualizadas pueden ser solicitadas a través de nuestra página web https://www.klsummit.com.

También puede pedirlas a su interlocutor habitual en Klüber Lubrication.

Datos técnicos	RPE-32	RPE-46	RPE-68	RPE-100
Número de artículo	340524	340525	340526	340527
Appearance	clear	clear	clear	clear
Colour space	colourless	colourless	colourless	colourless
Density	-	-	-	-
Density, 20°C	approximately 0.977 g/cm³	approximately 0.978 g/cm³	approximately 0.977 g/cm³	approximately 0.974 g/cm³
Fire point	-	-	-	-
Fire point, Cleveland open cup	-	-	-	-
Flash point	-	-	-	-
Flash point, Cleveland open cup	-	-	-	-
Flash point, ASTM D92, Cleveland open cup	≥ 230 °C	≥ 240 °C	≥ 250 °C	≥ 260 °C
Kinematic viscosity, 100°C	-	-	-	-
Kinematic viscosity, 40°C	-	-	-	-
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approximately 5.9 mm²/s	approximately 7.3 mm²/s	approximately 9.5 mm²/s	approximately 11.9 mm²/s
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approximately 33 mm²/s	approximately 47 mm²/s	approximately 70 mm²/s	approximately 102 mm²/s
Viscosity index	-	-	-	-
Viscosity index, ASTM D2270	approximately 120	approximately 119	approximately 115	approximately 107
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346	approximately -51 °C	approximately -49 °C	approximately -43 °C	approximately -40 °C
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-	-	-	-
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	60 months	60 months	60 months

RPE Series

Datos técnicos	RPE-120	RPE-170	RPE-220
Número de artículo	340375	340343	340285
Appearance	-	-	-
Colour space	-	-	-
Density	0.96 g/cm³	0.97 g/cm³	0.967 g/cm³
Density, 20°C	-	-	-
Fire point	310 °C	-	300 °C
Fire point, Cleveland open cup	-	approximately 332 °C	-
Flash point	240 °C	-	270 °C
Flash point, Cleveland open cup	-	approximately 255 °C	-
Flash point, ASTM D92, Cleveland open cup	-	-	-
Kinematic viscosity, 100°C	12.6 mm²/s	16.5 mm²/s	18.8 mm²/s
Kinematic viscosity, 40°C	121.4 mm²/s	171.5 mm²/s	215 mm²/s
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	-	-	-
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	-	-	-
Viscosity index	95	101	98
Viscosity index, ASTM D2270	-	-	-
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346	-	-	-
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-34 °C	-33 °C	-25 °C
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	60 months	60 months

Información de producto

RPE Series

Summit Lubrication

Übersetzen!!! Your expert in specialty lubricants. Since 1982, we have partnered with you to bring you the right solution and advanced lubrication technologies. With over 500 products, from air and gas compressor oils to refrigeration oils, we develop top-of-the-line products tailored to your specific needs. Your success is our success.

Summit Lubrication a brand of Klüber Lubrication NA LP /
9010 County Road 2120, Tyler, TX 75707 USA /
Phone: +1 800 749 5823 / www.klsummit.com

Los datos de este documento están basados en nuestros conocimientos y experiencias en el momento de la publicación y tienen como objetivo facilitar al lector técnicamente experimentado informaciones sobre posibles aplicaciones. Sin embargo no constituyen ninguna garantía ni de las características del producto ni de su adecuación y tampoco eximen al usuario de la obligación de efectuar ensayos prácticos con el lubricante seleccionado antes de aplicarlo. Todos los datos son valores orientativos que dependen de la composición del lubricante, de la aplicación prevista y de la técnica de aplicación. Los datos técnicos de lubricantes cambian según el tipo de las cargas mecánicas, dinámicas, químicas y térmicas y en función de la presión y del tiempo. Estos cambios pueden repercutir en la función de componentes. Recomendamos un asesoramiento personalizado y así mismo ponemos gustosamente a su disposición, muestras que tengan a bien solicitarnos. Los productos Klüber están sujetos a un desarrollo continuo. Por ello Klüber Lubrication se reserva el derecho de cambiar todos los datos técnicos de este documento en cualquier momento y sin aviso previo.

Editor y Copyright: Klüber Lubrication NA LP. Sólo está autorizada la reproducción total o parcial, previa consulta con Klüber Lubrication NA LP siempre que se indique la procedencia y enviando un ejemplar de prueba.