

SBL FG Series

Synthetic blower lubricants



Your benefits at a glance

- Extended lubricant life (up to 4,000 hours with oil analysis)
- Reduced operating temperatures
- Better corrosion protection
- Enhanced low and high temperature lubricating properties
- Longer blower life with reduced wear
- Lower maintenance costs

Your requirements - our solution

Summit SBL Food Grade Series synthetic lubricants are formulated to provide maximum lubrication protection and service for all positive displacement blowers including Roots, Gardner-Denver, Sutorbilt and Duroflow. The SBL synthetic lubricants exceed the

specification requirements for all of the major manufacturers of positive displacement blowers and are compatible with most commonly used seal materials.

These fully synthetic lubricants are NSF Registered and meet USDA 1998 (H1) guidelines (lubricants with incidental food contact). Summit is an ISO 21469 certified facility.

Material safety data sheets

Material safety data sheets can be requested via our website <https://www.klsummit.com>. You may also obtain them through your contact person at Summit Lubrication.

Characteristics	SBL-100F	SBL-220F	SBL-320F
Article number	340313	340142	340144
Service temperature, lower limit	-35 °C	-	-
Service temperature, upper limit	135 °C	-	-
Demulsifying capacity, DIN ISO 6614 /ASTM D1401, 82°C	40-40-0 (10) ml (min)	-	-
Density	0.837 g/cm ³	0.848 g/cm ³	0.852 g/cm ³
Density, 20°C	approx. 0.837 g/cm ³	-	-
Flash point	-	260 °C	260 °C
Flash point, ASTM D92, Cleveland open cup	≥ 240 °C	-	-
Foam test, ISO 6247 / ASTM D892, 24°C, sequence I	≤ 150/10 ml	-	-
Foam test, ISO 6247 / ASTM D892, 24°C, sequence III	≤ 150/10 ml	-	-
Foam test, ISO 6247 / ASTM D892, 93.5°C, sequence II	≤ 75/10 ml	-	-
ISO viscosity grade, DIN ISO 3448, ISO VG	100	-	-
Kinematic viscosity, 100°C	-	26.4 mm ² /s	32.8 mm ² /s
Kinematic viscosity, 40°C	-	233 mm ² /s	303 mm ² /s
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 100°C	approx. 14.4 mm ² /s	-	-
Kinematic viscosity, DIN EN ISO 3104 / DIN 53000-1, based on standard / ASTM D445 / ASTM D7042, 40°C	approx. 104 mm ² /s	-	-
Viscosity index	-	146	150
Viscosity index, ASTM D2270	approx. 143	-	-

SBL FG Series

Synthetic blower lubricants



Characteristics	SBL-100F	SBL-220F	SBL-320F
Copper corrosion	-	1 - - corrosion degree	1 - - corrosion degree
Copper corrosion, ASTM D130, 24 h, 100°C	1 - 100 - 24 corrosion degree	-	-
Steel corrosion, DIN ISO 7120 / ASTM D665, method A, 24 h, 60°C	rust-free	-	-
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346	approx. -54 °C	-	-
Pour point, DIN ISO 3016, ASTM D97, ASTM D5950, ASTM D7346, based on standard	-	-42 °C	-42 °C
FZG scuffing test, DIN ISO 14635-1, A / 8.3 / 90, failure load stage	≥ 12	-	-
Mineral Oils associated with, MOAH (Mineral Oil Aromatic Hydrocarbons), (Information based on recipe. The presence of impurities, cannot be ruled out.)	Component of recipe	-	-
Mineral Oils associated with, MOSH (Mineral Oil Saturated Hydrocarbons), (Information based on recipe. The presence of impurities, cannot be ruled out.)	Component of recipe	-	-
Minimum shelf life from the date of manufacture - in a dry, frost-free place and in the unopened original container, approx.	60 months	60 months	60 months

Summit Lubrication

Your expert in specialty lubricants. Since 1982, we have partnered with you to bring you the right solution and advanced lubrication technologies. With over 500 products, from air and gas compressor oils to refrigeration oils, we develop top-of-the-line products tailored to your specific needs. Your success is our success.

Summit Lubrication a brand of Klüber Lubrication NA LP /
9010 County Road 2120, Tyler, TX 75707 /
Phone: +1 800 749 5823 / www.klsummit.com

The data in this document is based on our general experience and knowledge at the time of publication and is intended to give information of possible applications to a reader with technical experience. It constitutes neither an assurance of product properties nor does it release the user from the obligation of performing preliminary field tests with the product selected for a specific application. All data are guide values which depend on the lubricant's composition, the intended use and the application method. The technical values of lubricants change depending on the mechanical, dynamical, chemical and thermal loads, time and pressure. These changes may affect the function of a component. We recommend contacting us to discuss your specific application. If possible we will be pleased to provide a sample for testing on request. Klüber products are continually improved. Therefore, Klüber Lubrication reserves the right to change all the technical data in this document at any time without notice.

Publisher and Copyright: Klüber Lubrication NA LP. Reprints, total or in part, are permitted only prior consultation with Klüber Lubrication NA LP and if source is indicated and voucher copy is forwarded.